

Shandong Liwald Energy Technology Co., LTD

CI-4 15W40 test report

Execution standard: GB11122-2006

inspecting item	reference index		Inspection index	Determine the result
	CI-4 15W40			
Kinematic viscosity (40℃) m m ² / S	—		107.63	qualified
Kinematic viscosity (100℃) m m ² / S	12.5-16.3		13.91	qualified
Flash point (opening), °C	Not less than	205	220	qualified
pour point °C	Not higher than -30℃		-38	qualified
viscosity index	///		130	qualified
Low-temperature motility viscosity, mPa's (°C)			6900 (-20)	qualified
Water content,% (m / m)	No more than traces		not have	qualified
mechanical admixture	Not greater than 0.01		0.003	qualified
spumescence	///			qualified

Conclusion: qualified

Test by: Jiang Xiaohui

Reviewer: Li Changchun

January 08, 2025

